

DATASHEET STEAM CYLINDER SERIES 3000/SERIES 4

SABIC® PP 56M10, PP block copolymer for injection moulding

Description:

This grade has a high impact resistance, even at low temperatures, and a high stiffness. It is used in a variety of applications e.g. containers and crates & boxes. It is also used in automotive components, like for example battery cases.

Health, Safety and Food Contact regulations:

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC-europe.com>

TYPICAL VALUES

Properties	Unit (Si)	Values	Test methods
Polymer properties			
Melt flow rate (MFR)			ISO 1133
at 230°C and 2.16 kg	g/10 min	6.2	
Density	kg/m ³	905	ISO 1183
Mechanical properties			
Tensile test			ISO 527
stress at yield	MPa	32	
stress at break	MPa	30	
strain at break	%	600	
Flexural test			ASTM D 790
Flexural modulus	MPa	1550	
Izod impact notched			ISO 180/4A
at 23°C	kJ/m ²	10	
at 0°C	kJ/m ²	5.0	
at -20°C	kJ/m ²	4.0	
Charpy impact notched			ISO 179
at 23°C	kJ/m ²	10	
at 0°C	kJ/m ²	5.0	
at -20°C	kJ/m ²	3.0	
Hardness Shore D		68	ISO 868
Thermal properties			
Heat deflection temperature			
at 1.80 MPa (HDT/A)	°C	53	ISO 75/A
at 0.45 MPa (HDT/B)	°C	89	ISO 75/B
Vicat softening temperature			
at 10 N (VST/A)	°C	147	ISO 306/A
at 50 N (VST/B)	°C	77	ISO 306/B

Quality:

SABIC Europe is fully certified in accordance with the internationally accepted quality standard ISO 9001.

Storage and handling:

Avoid prolonged storage in open sunlight, high temperatures (<50°C) and / or high humidity as this could well speed up alteration and consequently loss of quality of the material and / or its packaging. Keep material completely dry for good processing.

Disclaimer: The information contained herein may include typical properties of our products or their typical performances when used in certain typical applications. Actual properties of our products, in particular when used in conjunction with any third party material(s) or for any non-typical applications, may differ from typical properties.

It is the customer's responsibility to inspect and test our product(s) in order to satisfy itself as to the suitability of the product(s) for its and its customers particular purposes. The customer is responsible for the appropriate, safe and legal use, processing and handling of all product(s) purchased from us. Nothing herein is intended to be nor shall it constitute a warranty whatsoever, in particular, warranty of merchantability or fitness for a particular purpose.

SABIC Europe as referred to herein means any legal entity belonging to the SABIC Europe group of companies.

Nordmann Engineering Ltd.

Talstrasse 35-37

CH-8808 Pfäffikon, Switzerland

Phone +41 55 416 66 06, Fax +41 55 416 62 46

info@nordmann-engineering.com

www.nordmann-engineering.com